

VINTAGE 'S'

For Vintage colors & Vintage 'F' please consult the respective technical data sheets .

PRODUCT DESCRIPTION

Ciranova Vintage 'S' is a waterborne reaction stain to give oak a smoked look. Vintage 'S' reacts with the tannin in the wood.

TECHNICAL DATA

DENSITY 1,1 KG/LT

CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010

PREPARATION

Sand the wood before with grit 100-120. After sanding the sanding dust must be carefully remove .

USER INSTRUCTIONS

Stir well before use. It is recommended to test the chosen color first before you treat the entire surface.

Apply the Vintage S generously with a lye-resistant brush or roller in the direction of the grain. Afterwards equalize the vintage S with a dry brush or cloth. Let the surface dry and rinse off with clean water.

DRYING TIME

Dry after + / - 8-16 hours

COVERAGE

+/- 20 m² / liter

AFTER-TREATMENT

After drying, the upstanding fiber a must be removed by polishing the surface with a white or beige pad.

Afterwards, the surface should be made dust-free so the vintage can be finished with Hardwaxoil from the Ciranova range. To finish with a varnish (Aquafix gamma) the Vintage must first be blocked with a Hardwaxoil Magic or Hardwaxoil Solid Full (Clear, Natural or Natural White).

PRODUCT

Shelf life: 1 year in closed original packaging.

SPECIAL REPORTS

Vintage S is not frost resistant, therefore do not use or transport below 5 ° c.

The product is corrosive. Don't use materials that can rust. The use of gloves and goggles is necessary The final color depends on the type of wood, sanding, and the applied amount. Therefore, it is recommended to always test the color on the wood!



5L

1L

Ciranova[®] products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

PRODUCED BY DEBAL COATINGS NV

Industrieweg 29 – B 8800 Beveren-Roeselare
tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48
www.ciranova.be ciranova@ciranova.be